**Eastern Chem Lac** 

33 Haynes Circle Chicopee, MA 01020 Telephone 413-592-6997 Facsimile: 413-594-7321



## W6880 CONDUCTIVE WASH PRIMER

GENERAL INFORMATION	PHYSICAL PROPERTIES	APPLICATION
A two component vinyl based, acid etch wash primer specifically designed as an adhesion promoter for CONDUCTIVE	1. Volume Solids: 3.4 +/- 2%	Can be applied using conventional air, airless, or HVLP.
topcoat paint systems over untreated ferrous and non ferrous substrates.	2. Theoretical Coverage @ 1 mil dft: 54 ft²/gallon	Substrate Preparation: Substrate must be clean and free of oils, grease, dirt or other contaminants prior to
W6880 will provide the proper base for adhesion to the substrate without inhibiting conductivity.	3. Dry Time: Set to Touch: 5 minutes To Handle: 10 – 15 minutes	application.  Apply a smooth wet film to the cleaned substrate.
	To Topcoat: 20 - 30 minutes Force Dry @ 150 – 180°F: Dry to Topcoat: 10 minutes	Safety Precautions: This product is intended for professional
	4. Dry Film Thickness: 0.2 – 0.4 mils	use in an industrial environment only.  Consult the Material Safety Data Sheet prior to application.
	5. Mix Ratio: 1 part W6880 1.5 parts X2649 Wash Primer Reducer	
	6. VOC: 6.5 lbs/gallon (781 grams/liter)	
	7. Pot Life: 8 hours	
Eastern Chem Lac warrants that its products meet its internal specifications and are of merchantable quality. However, the purchaser is solely responsible for the suitability of the product for any particular application. The purchaser should thoroughly test or qualify the product for serviceability, environmental compliance and health and safety factors prior to use. Further, our total liability is limited to the price of the product or replacement in kind.	8. Shelf Life: One Year	
Eastern Chem Lac 33 Haynes Circle Chicopee, MA 01020		
Phone: 413-592-6997 Fax: 413-594-7321 www.eclcoatings.com		

Revised: 1/26/2024